



LOCTITE[®] 55[™]

May 2006

PRODUCT DESCRIPTION

LOCTITE[®] 55[™] provides the following product characteristics:

| | |
|----------------------|---|
| Technology | Coated multifilament thread |
| Chemical Type | Polyamide thread with inert proprietary paste |
| Appearance | White colored, coated cord ^{LMS} |
| Cure | Not applicable |
| Application | Thread sealing |

LOCTITE[®] 55[™] is a general purpose, threaded pipe and fitting sealant which is wound from the dispensing package onto the threads of the pipe. It is supplied in containers, which serve for both storage and dispensing purposes. Recommended for sealing metal and plastic tapered pipe threads and fittings up to 4" NPT (National Pipe Thread) for use in industrial applications in aqueous and non-aqueous fluids. Particularly suitable in threaded assembly applications that require immediate use and may undergo small readjustments before use. This product is typically used in applications up to 149 °C.

UL Classification

Classified by Underwriters Laboratories Inc.[®] for use on threaded joints of metal pipes not exceeding 1-1/2 inch pipe size in devices handling gasoline, petroleum oils and not exceeding 1 inch pipe size in devices handling natural gas (pressures not over 2.07 MPa), propane and butane.

NSF International

Certified to ANSI/NSF Standard 61 for use in commercial and residential potable water systems not exceeding 82° C.

CSA International

Certified to CSA International Class 3319-01 & 3319-81 for use with natural and liquified petroleum gases (vapor state) and intended for use at ambient temperatures of -54 °C to +149 °C with a maximum pressure rating of 2.07 MPa.

EN 751-2

Sealing materials for metallic threaded joints in contact with 1st, 2nd, and 3rd family gases and hot water; Part 2: Non-hardening jointing compounds. LOCTITE[®] 55[™] has been tested and conforms to EN 751-2 for a class ARp compound and carries the **DVGW** approval.

WRC and KTW approval

Suitability of non-metallic products for use in contact with water intended for human consumption with regard to their effect on the quality of the water. LOCTITE[®] 55[™] has been tested and has potable water approval to BS 6920 and also meets the specifications of the **WRC** and **KTW** for both cold and hot potable water.

TYPICAL PROPERTIES

| | |
|---|-------------------------------|
| Specific Gravity @ 25 °C | 1.25 |
| Flash Point - See MSDS | |
| Coating Weight, g/m | 0.54 to 0.74 ^{LMS} |
| Spool Weight, g: | |
| 12 meter spool | 7.0 to 10.4 ^{LMS} |
| 50 meter spool | 27.3 to 39.6 ^{LMS} |
| 100 meter spool | 54.0 to 80.7 ^{LMS} |
| 150 meter spool | 81.0 to 118.4 ^{LMS} |
| Spool Length, m: | |
| 12 meter spool | 12.5 to 14.0 ^{LMS} |
| 50 meter spool | 50.5 to 53.5 ^{LMS} |
| 100 meter spool | 101.0 to 109.0 ^{LMS} |
| 150 meter spool | 151.0 to 159.0 ^{LMS} |
| Lubricity, ASTM D5648, K value: | |
| 3/8 x 16 fastener, using LOCTITE [®] 55 [™] | 0.15 |
| 3/8 x 16 fastener (degreased) | 0.2 |
| 3/8 x 16 phosphate and oil nuts and bolts | 0.16 |

(In critical applications, it is necessary to determine the K values independently. Henkel corporation makes no warranty of specific performance on any individual fastener):

TYPICAL PERFORMANCE OF APPLIED MATERIAL

Approval tests according to EN 751-2 for class ARp compound:

| | |
|--|----------|
| Soundness Test, section 7.2.1.2 | No leaks |
| Soundness Test after 45° joint adjustment, section 7.2.1.3 | No leaks |
| Resistance to gas condensates, section 7.2.1.4 | No leaks |
| Hot water resistance test, section 7.2.1.5 | No leaks |
| Temperature cycling test, section 7.2.1.6 | No leaks |
| Vibration test, section 7.2.1.7 | No leaks |
| Compatibility with foam forming leak tester, section 7.2.2 | Pass |
| Test of hardening and dismantling, section 7.2.3 | Pass |

Pressure Resistance

LOCTITE[®] 55[™] was successfully tested for pressure resistance and sealability to 69 MPa. 3/8 NPT steel pipe tees and plugs were assembled and pre-torqued to 27 N·m prior to testing at 69 MPa hydraulic pressure @ 23 °C according to ASTM D 1599.

TYPICAL ENVIRONMENTAL RESISTANCE

LOCTITE[®] 55[™] has resistance to most common industrial fluids and gasses.

Steam Compatibility

LOCTITE[®] 55[™] was successfully tested for steam compatibility to 0.17 MPa. 1.5 " NPT were assembled and tested at 0.17 MPa pressure @ 130 °C for 1,000 hours.

GENERAL INFORMATION

This product is not recommended for use in pure oxygen and/or oxygen rich systems and should not be selected as a sealant for chlorine or other strong oxidizing materials.

For safe handling information on this product, consult the Material Safety Data Sheet (MSDS).

Directions for use

1. Clean parts with a wire brush prior to application of product.
2. Hold the end of the Pipe Sealing Cord against the male nipple with one finger approximately two threads away from the end.
3. Wind the fiber onto the pipe threads in the same direction of the thread helix starting from the end of the pipe. For optimum performance, the grooves of the threads should be filled without completely masking the pitches of the thread.
NOTE: It is not necessary to follow the valley of the thread.
4. **CAUTION:** Do not over-apply the Pipe Sealing Cord. Excessive material tends to be pushed off as fittings are assembled, and it also becomes mechanically more difficult to complete the engagement.
5. Cut the required length off with the integrated cutting tool and smooth the loose end onto the pitches of the pipe thread.
6. LOCTITE® 55™ can be adjusted up to 90° after tightening.

Usage/Application Information

The following is a guideline for how much LOCTITE® 55™ to use per pipe diameter.

| Pipe Diameter | Number of turns (wraps) | |
|---------------|-------------------------|----------|
| | Metal | Plastic |
| ½ " | 6 to 8 | 12 to 15 |
| ¾ " | 7 to 9 | 15 to 25 |
| 1 " | 8 to 12 | 20 to 30 |
| 1½ " | 10 to 15 | 25 to 35 |
| 2 " | 15 to 25 | ----- |
| 2½ " | 20 to 30 | ----- |
| 3 " | 25 to 35 | ----- |
| 3½ " | 30 to 40 | ----- |
| 4 " | 35 to 45 | ----- |

LOCTITE® 55™ provides sealing against cold water and compressed air on plastic pipe threads when applied properly in a sufficient amount.

Loctite Material Specification^{LMS}

LMS dated January 26, 2005. Test reports for each batch are available for the indicated properties. LMS test reports include selected QC test parameters considered appropriate to specifications for customer use. Additionally, comprehensive controls are in place to assure product quality and consistency. Special customer specification requirements may be coordinated through Henkel Quality.

Storage

Store product in the unopened container in a dry location. Storage information may be indicated on the product container labeling.

Optimal Storage: 8 °C to 21 °C. Storage below 8 °C or greater than 28 °C can adversely affect product properties.

Material removed from containers may be contaminated during use. Do not return product to the original container. Henkel Corporation cannot assume responsibility for product which has been contaminated or stored under conditions other than those previously indicated. If additional information is required, please contact your local Technical Service Center or Customer Service Representative.

Conversions

$(^{\circ}\text{C} \times 1.8) + 32 = ^{\circ}\text{F}$
 $\text{kV/mm} \times 25.4 = \text{V/mil}$
 $\text{mm} / 25.4 = \text{inches}$
 $\mu\text{m} / 25.4 = \text{mil}$
 $\text{N} \times 0.225 = \text{lb}$
 $\text{N/mm} \times 5.71 = \text{lb/in}$
 $\text{N/mm}^2 \times 145 = \text{psi}$
 $\text{MPa} \times 145 = \text{psi}$
 $\text{N}\cdot\text{m} \times 8.851 = \text{lb}\cdot\text{in}$
 $\text{N}\cdot\text{m} \times 0.738 = \text{lb}\cdot\text{ft}$
 $\text{N}\cdot\text{mm} \times 0.142 = \text{oz}\cdot\text{in}$
 $\text{mPa}\cdot\text{s} = \text{cP}$

Note

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, **Henkel Corporation specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Henkel Corporation's products. Henkel Corporation specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits.** The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Henkel Corporation patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more United States or foreign patents or patent applications.

Trademark usage

Except as otherwise noted, all trademarks in this document are trademarks of Henkel Corporation in the U.S. and elsewhere. ® denotes a trademark registered in the U.S. Patent and Trademark Office.

Underwriters Laboratories, inc.® is a trademark of Underwriters Laboratories, inc.

Reference 1.5